

CORROSIONS-RESISTANT STEELS - AUSTENITIC STEELS AND NON MAGNETIC STEELS

Application Segments

[Engineering](#)
[Oil & Gas / CPI](#)

Available Product Variants

[Long Products*](#)
[Semi-Finished Products / Billet](#)
[Plates](#)
[Open Die Forgings](#)

* Presented data refer exclusively to long products. Please observe the detailed explanations at the end of the data sheet (pdf).

Product Description

BÖHLER P501 is a highly corrosion-resistant, nitrogen-strengthened Cr-Ni-Mo-N steel that is characterised by its resistance to corrosion in seawater and very good resistance to intergranular corrosion and stress corrosion cracking. Due to the alloy design, the yield strength is significantly higher than that of a comparable Cr-Ni-Mo stainless steels and a stable austenitic microstructure is achieved, so that the steel remains non-magnetisable even after cold forming and has the lowest magnetic permeability. In addition to its original application as a hull and structure for submarines, BÖHLER P501 is also used for magnetic shielding and components in the oil and gas industry, for example.

Process Melting

[Airmelted](#)

Applications

- > Drilling tools and components
 - > Well Completion Tools
- > Other Components
 - > Well Logging Tools
- > Other Power Generation Components

Technical data

Material designation		Standards	
1.3964	SEL	SEW 390	Others
X2CrNiMoNNb21-16-5-3	EN		
S20910	UNS		

Chemical composition (wt. %)

C	Si	Mn	P	S	Cr	Mo	Ni	Nb	N
max. 0.030	max. 1.0	4.0 to 6.0	max. 0.025	max. 0.010	20.0 to 21.5	3.0 to 3.5	15.0 to 17.0	max. 0.25	0.20 to 0.35

Related to SEW 390

Delivery condition

Round Bars and Wire Rod (if any)

		Diameter mm	
ROLLED			
5.00	-		130.00
FORGED			
130.10	-		300.00

More information regarding MOQ, lengths and tolerances upon request.

Physical Properties

Density	7.9	[kg/dm ³]
Thermal conductivity	14	[W/(m.K)]
Specific heat	460	[kJ/kg K]
Spec. electrical resistance	0.8	[Ohm.mm ² /m]

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25
8605 Kapfenberg, AT
T. +43/50304/20-0
E. info@bohler-edelstahl.at
<https://www.voestalpine.com/bohler-edelstahl/de/>