

# ACEROS PARA TRABAJO EN FRÍO

## Formatos disponibles

Productos largos\*

Chapas

\* ) Presented data refer exclusively to long products. Please observe the detailed explanations at the end of the data sheet (pdf).

## Descripción

Acero para herramientas de estampación en frío, herramientas para acuñar monedas, cuchillería, herramientas de fresado, cuchillas de corte en frío para material de calibre pesado y moldes de plástico.

## Método de obtención

Convencional

## Propiedades

- > Dureza y Ductilidad : alto
- > Estabilidad dimensional : buena

## Aplicaciones

- > Cuchillas de máquinas (fabricantes)
- > Corte fino / Troquelado / Estampado
- > Componentes para la industria del reciclaje
- > Conformado en frío
- > Componentes estándar (moldes, placas, expulsores, punzones)
- > Acuñado
- > Componentes generales de ingeniería mecánica

## Datos técnicos

Designación	
~1.2721	SEL
~50NiCr13	EN

## Composición Química

C	Si	Mn	Cr	Mo	Ni
0,55	0,30	0,40	1,00	0,25	3,00

## Características

	Resistencia a la compresión	Estabilidad dimensional durante el tratamiento térmico	Tenacidad	Resistencia al desgaste abrasivo
<b>BÖHLER K605</b>	★★	★★★	★★★★★	★
<b>BÖHLER K305</b>	★★★★★	★★★	★★	★★★★★
<b>BÖHLER K306</b>	★★★★★	★★★	★★★★★	★★★★
<b>BÖHLER K313</b>	★★★★★	★★★	★★★	★★★★
<b>BÖHLER K320</b>	★★★	★★★	★★★	★★★★
<b>BÖHLER K329</b>	★★★	★★★	★★★★★	★★★★★
<b>BÖHLER K600</b>	★	★★★	★★★★★★	★
<b>BÖHLER K601</b>	★	★★★	★★★★★	★★

## Estado de suministro

### recocido

Dureza (HB)	máx. 250
-------------	----------

## Tratamiento térmico

### Recocido

Temperatura	610 a 650 °C	Slow controlled cooling in furnace at a rate of 50 to 68°F/hr (10 to 20°C/hr) down to approx. 1112°F (600°C), further cooling in air.
-------------	--------------	---------------------------------------------------------------------------------------------------------------------------------------


### Alivio de tensiones

Temperatura	650 °C	Slow cooling in furnace. Intended to relieve stresses set up by extensive machining, or in complex shapes. After through heating, hold in neutral atmosphere for 1 - 2 hours.
-------------	--------	-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

### Temple y revenido

Temperatura	840 a 870 °C	Air, Oil Holding time after temperature equalization: 15 to 30 minutes. After hardening, tempering to the desired working hardness, see tempering chart.
-------------	--------------	----------------------------------------------------------------------------------------------------------------------------------------------------------


**Tempering chart**



**Tempering:**

Hardening temperature: 850°C  
 Specimen size: square 20 mm


**Continuous cooling CCT curves**



Austenitising temperature: 1544°F (840°C)  
 Holding time: 20 minutes

O Vickers hardness  
 3...99 phase percentages  
 0.47...19.7 cooling parameter, i.e. duration of cooling from 1472 to 932°F (800 to 500°C) in  $s \times 10^{-2}$   
 33,8...32,36°F/min (1...0.2K/min) cooling rate in °F/min (K/min) in the 1472 to 932°F (800 to 500°C) range.

**Quantitative phase diagram**




A... Austenite  
 B... Bainite  
 F... Ferrite  
 K... Carbide  
 M... Martensite  
 P... Pearlite  
 RA... Retained austenite

--- Oil cooling  
 - - - Air cooling


1... Edge or face  
 2... Core

**Isothermal TTT curves**




Austenitising temperature: 840°C / 1544°F  
 Holding time: 20 minutes

**Influence of work diameter on core hardness and hardness penetration**



Quenched from: 850°C / 1562°F  
Agent: Oil

**Heat treatment sequence**



## Propiedades físicas

Temperatura (°C)	20
Densidad (kg/dm <sup>3</sup> )	7,85
Conductividad térmica (W/(m.K))	28
Calor específico (kJ/kg K)	0,46
Resistencia eléctrica específica (Ohm.mm <sup>2</sup> /m)	0,3
Módulo de elasticidad (10 <sup>3</sup> N/mm <sup>2</sup> )	210

## Expansión térmica

Temperatura (°C)	100	200	300	400	500
Expansión térmica (10 <sup>-6</sup> m/(m.K))	11	12,5	13	13,5	14

**Long Products:** For additional specifications and technical requirements, please contact our regional voestalpine BÖHLER sales companies.

**Sheet & Plates:** Product Variant may differ in terms of melting process, technical data, delivery, and surface condition as well as available product dimensions. Please contact voestalpine BÖHLER Bleche GmbH & Co KG.

*The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.*